

DUROPROOF™ BLF

Fibre Reinforced Roof and Gutter Lining

DUROPROOF™ BLF is a fibreglass reinforced roof repair compound used to maintain and repair most roofs and gutters. **DUROPROOF™ BLF** is ideal for leaking box gutters, even emergency repairs in rain. **DUROPROOF™ BLF** forms a flexible fibre reinforced waterproof lining to all common building materials-metal, asbestos, slate, felt, asphalt, concrete, wood and plastic with typical service life of 5 -10 years.

PRINCIPLE CHARACTERISTICS

- Resistant to weathering, waterproof
- Simple application
- Flexible, fast cure
- Long life, cost effective

USE AREAS

- Maintenance and repair of metal or fibro / asbestos roofs, gutters, flashings
- Concrete roof decks and concrete gutters
- Retaining walls, tanking and metal flashings

APPLICATION

Thoroughly clean and remove all loose dirt, rust, oil, flaking paint to give a sound surface.

Apply **DUROPROOF™ BLF** liberally by brush and roller spreading the compound to a thickness of approx 1.5-2.0mm, taking care to work the compound well into the surface. Spread evenly before the material begins to dry. Two coats may be necessary to ensure an adequate dry film thickness, particularly on rusted surfaces. Rust holes and splits are repaired by laying fiberglass into the first coat, then applying a further coat.

CLEAN UP

Use mineral turps

PRECAUTIONS

During application, wear protective clothing, ensure adequate ventilation and eliminate ignition sources. Highly flammable in wet state. **Refer Durotech MSDS prior to use.**

GENERAL

Colour	Black	
Weather Resistance	Very good. Surface will chalk slightly with exposure. For improved U.V. Protection, top coat with acrylic or aluminium paint.	
Dry Time	Touch dry 40mins @ 25°C	
Re-Coat	After 40mins @ 25°C	
Coverage	2 coats each at 0.75ltrs/m ² [1.3m ² /Litre]	
Wet Film Thickness	Per coat 0.75mm thick	
Dry Film Thickness	1.0mm total	
Solids Content	59%	
Shelf Life	1 year in unopened container stored @ 20°C	

PACKAGING

- 10 Litre
- 4 Litre



Waterproofing Compound

Durotech Industries 14 Essex Street, P.O Box 5092, Minto, NSW 2566
Telephone: +61 2 9603 1177 Fax: +61 2 9603 3796 Technical 1300 791 177
 Email: sales@durotechindustries.com.au Web: www.durotechindustries.com.au

DUROTECH

The information provided in this technical bulletin is as correct in detail as possible and is intended to give a fair description of the product and its capabilities. In practice, the substrate and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and that the product is not used beyond its physical limitations. The product is guaranteed providing that it is applied in accordance with the manufacturer's instructions as stated in this data sheet and any relevant Standard or Code and provided that the building and installation is structurally sound. Durotech terms and conditions of sale apply.