



DUROPROOF ZR PRIMER

GENERAL PURPOSE IRON OR STEEL PRIMER

Duroproof[®] ZR Primer is a brushable general purpose, oil based interior/exterior primer suitable for use on iron or steel surfaces

PRINCIPLE CHARACTERISTICS

May be used as an anti-corrosive primer on steel and wrought, cast or weathered galvanised iron. As it doesn't contain lead it may be used on roofs, under approved coatings used for drinking water collection.

SURFACE PREPRATION

Previously Painted Surfaces: Remove loose and flaking paint. Wash off dirt and mould with Sugar Soap, diluted as recommended. Remove rust and scale by scraping, sanding or treating with a rust remover or dissolver.

Unpainted Steel, Wrought Iron: Scrape, grind off mill scale, welding slag, etc. Degrease and remove any remaining rust by scraping, sanding or by treating with a rust remover or dissolver.

Weathered Galvanised Iron: Wash with detergent, rinse and dry.

APPLICATION

Apply two coats of primer by brush, allowing 16 hours @ 25°C between coats. (The second coat is recommended to reduce the risk of spot rusting). Do not leave the primer for more than 7 days before top coating. Top coat with Duro Mastic™ AC, Duraroom™ or Durarmor™, or consult Durotech for advice.

THINNING & CLEAN UP

Durotech ZR Primer should be applied without thinning by brush or roller. If spraying, reduce with approximately 100ml of Mineral Turpentine or Xylene per litre. Equipment should be cleaned immediately after use with Mineral Turpentine or Durotech Xylene.

PRECAUTIONS

Refer to Durotech MSDS prior to use. Do not apply below 10°C and above 30°C.

GENERAL

Colour	Grey
Dry Time	2-4 hours @25°C
Recoating	16 hours @ 25°C
Coverage	10 m ² /L
Shelf Life	12 months in unopened container @ 20°C

PACKAGING

- ◆ 4 Litre
- ◆ 20 Litre



14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177

+61 2 9475 5059

sales@durotechindustries.com.au

www.durotechindustries.com.au