

DUROPOND BLACK



DESCRIPTION

Duropond Black is a Water based Class III membrane based on heavy duty SBR compound and well balance particle size distribution of tough inert fillers that will provide a seamless watertight membrane for waterproofing ponds, water features and areas under permanent wet conditions.

FEATURES

- Fast drying and easy to repair
- Water-based, pre-mixed -ready and easy to use and easy clean up
- Environmentally friendly – low VOC
- Good crack bridging properties and permanent flexible to accommodate structural movement
- Excellent water resistance
- Excellent adhesion to substrate

USES

- Ponds
- Ornamental water features
- Tanking

LIMITATIONS

- Not to be used directly to impervious or non-porous substrates.
- Not suitable for use in chlorinated water
- Cannot be used to areas directly exposed to sunlight.
- Cannot be applied over damp or wet substrates.
- Not suitable for negative head of water pressure.

COLOURS

- Black

TECHNICAL INFORMATION

Appearance	Heavy thick and high viscous liquid membrane
Odour	mild
Solid content (weight)	61%
Solid content (volume)	56%
Density	1.243 kg/li
Dry to handle per coat (@22°C / 50% RH)	60 minutes
Recoat time per coat (@22°C / 50% RH)	3 - 4 hours
VOC (calculated)	5.065 g/l
Shore "A" hardness	Approx. 70
Elongation	400%
Tensile Strength	1.0 MPa
Membrane Rating	Class 3
Flammability	Non-flammable

SUITABLE SUBSTRATES

- Concrete
- Cement Render
- Brickwork
- Blockwork

PACKAGING

- Available in a 4L, 15L pail



COVERAGE

Coverage rate will depend on the porosity of the substrate. Minimum of Two coats are recommended to get the optimum performance

Minimum 1.0 m²/li per coat applied at minimum 1000 um wft

SHELF LIFE

Approximately 12 months in unopened containers stored in a cool, dry place.

SURFACE PREPARATION

- Surfaces must be clean, dry and free from voids, laitance, grease, oil, wax, curing compounds, coatings, adhesive residues or any loose contaminating material.
- New Concrete substrates must be allowed to cure for a minimum of 28 days while renders and screed must have cured for 7 days. Concrete substrates must not contain moisture greater than 4.5%. Use Tramex CME 4 Moisture Meter. Additional concrete testing maybe be required depending on concrete construction and jobsite location.
- If minor consolidation is required, apply one coat of 1:1 dilution of Duropond and water and allow to dry.
- If pond or water feature is in-ground, 2 coats of 2K Moisture barrier primer, Duromix Hibuild WBE, must be used to seal concrete slabs subject to a hydrostatic head of pressure from the negative side. Moisture Barrier primer must be clean, dry and smooth immediately prior to membrane application.
- A reactive mineral primer/sealer must be applied as a primer coat on all applications to porous or semi porous cementitious substrates that requires greater amount of surface consolidation.

Membranes should not be applied until substrates suitability has been assessed and all preparation steps have been completed.

MIX PREPARATION

It is a premix product and ready to use.

However, if products have been stored longer, condensation may occur. Stir contents thoroughly before and during use.

APPLICATION

Apply membrane according to the recommended coverage rate with paintbrush or roller. Allow the first coat to dry for a minimum of 2 hours and a maximum of 6 hours, at temperatures of 22°C and above but below 35°C before recoating. Longer drying times will be required at lower temperatures. Drying times will vary depending on humidity, surface temperature and porosity of substrates.

CLEAN-UP & RETURN TO SERVICE

Water can be used to clean up excess product, spills and tools while product is wet. When fully cured, tools and spills can be only removed mechanically.

HEALTH & SAFETY PRECAUTIONS

- Duropond Black is a non-hazardous and non-dangerous product.
- The Safety Data Sheet (SDS) must be read and understood prior to use.

Durotech Industries

VICTORIA

34 Indian Drive Keysborough
Victoria 3173

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

NEW SOUTH WALES

14 Essex st, Minto, Sydney
NSW 2566

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

QUEENSLAND

16 Export Drive Molendinar,
Gold Coast 4214

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

SOUTH AUSTRALIA

348 Richmond Road
Netley Australia

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attachments and suggests that the recipient check this document and any attached files for the presence of viruses."



@DUROTECHINDUSTRIES.COM.AU