

DUROTECH WRP CONCRETE SEALER



PENETRATIVE SEALER AND WATERPROOFING LIQUID

DESCRIPTION

Durotech WRP Concrete Sealer is a clear, high pH, deep penetrating siloxane waterproofing solution. Durotech WRP Concrete Sealer penetrates into the tissue of porous substrates and creates a waterproofing barrier below the surface preventing the ingress of water. Durotech WRP Concrete Sealer is an effective waterproofing solution and stops leaks without lifting tiles or changing the overall appearance of the surface. Durotech WRP Concrete Sealer also solves the problems associated with water penetration such as corrosion of steel reinforcement, friability and binder loss of surfaces, fungal and bacteria attack and degradation due to carbon dioxide permeability. Durotech WRP Concrete Sealer is capable of withstanding high pH conditions such as found in new concrete and lime-based mortars and bricks. Durotech WRP Concrete Sealer still allows the diffusion of vapours or 'breathing' ability of the substrate.

BENEFITS AND ADVANTAGES

- Forms a waterproofing barrier without changing the overall appearance of the surface.
- Seals tile beds without lifting tiles.
- Highly economic solution.
- Long lasting protection.
- Quick drying.
- Dries clear in a flat (low gloss) finish.
- It can be re-coated.
- Using WRP Concrete Sealer is a very viable and economical first effort attempt to stop leaks.
- Provides excellent weatherproof barrier to rain and salt spray.
- Provides an anti-graffiti barrier.

USES

- Waterproofing external concrete, cement, cement render, face brick, block walls, sandstone, porous pavers and other porous surfaces.
- Prevention or minimization of efflorescence and laitance (white salt spotting or leaching).
- Protection of sandstone.
- General rainwater barrier.
- Assists in preventing mold and fungus growth.
- Anti-graffiti protection (sacrificial coating).

SUITABLE SURFACES

- Concrete
- Cement
- Cement Render
- Block Work
- Face Bricks
- Porous Pavers
- Grout (tiled areas)
- Sand and cement tile beds,
- Sandstone
- Terracotta Pavers
- Other Porous Surfaces

Advice from Durotech should be sort for the most appropriate priming method for these surfaces; Durotech has a recommended system for all of the above.



SPECIFICATION

The information contained in this product data sheet is typical but does not constitute a full specification as conditions and specific requirements may vary from project to project. The instructions should be considered as a minimum requirement but the applicator or contractor must use their skill, knowledge and experience to carry out additional works as may be necessary to meet the requirements of the project. Specification for specific projects should be sought from the Company in writing.

LIMITATIONS

- Durotech WRP Concrete Sealer penetrates into the tissue of the substrates and accordingly relies its soundness and stability.
- Durotech WRP Concrete Sealer will not bridge or seal cracks.
- For Durotech WRP Concrete Sealer to work effectively, sufficient product must be absorbed into the surface to fill the voids within the substrate. Highly porous, sandy and friable surface may not contain sufficient density to allow the Durotech WRP Concrete Sealer to create an adequate 'build-up' of WRP Concrete Sealer to form waterproofing barrier. Test area are highly recommended.
- The quantity of WRP Concrete Sealer needed for a given area is subject to its density, porosity, thickness, soundness and condition which may not be apparent.

As an Anti-Graffiti Coating

- The surface must be very well saturated so that a layer of the cured coating lays across the surface. Inadequate saturation and coverage will negate or diminish the effectiveness of the product as an anti-graffiti coating.

PRECAUTIONS IN USE

When applying Durotech WRP Concrete Sealer it is strongly recommended that all safety precautions are followed as per product label and data sheet. As the product contains solvent ensure that all sources of ignition are kept away. Ensure area is well ventilated. Adequate masks should be worn when spraying. Protect surrounds against over spray. Observe all precautions on the Safety Data Sheet. In exposed areas, do not apply if rain is imminent and protect coating from rain and inclement weather until fully cured. As a precaution, we suggest that, at least initially, the surface may be slippery if wet.

SURFACE PREPARATION

Good preparation is essential. Surfaces must be sound, stable, dry, clean and free of dust, loose, flaking, friable material and substances that may diminish adhesion.

All surfaces must be clean, dry, of sound construction, stable and free of any dust, dirt, grease, oil, curing compounds or contaminants that might interfere with adhesion.

Cracks must be repaired. If mortar is suitable then use a non-shrink mortar. If flexibility is required to repair the crack, this should be done after the application of Durotech WRP Concrete Sealer as the solvent may pit or slightly dissolve the sealant.

Loose grout must be removed and then replaced with sound grouting and allowed to dry.

Ensure surfaces are clean, free of other coatings such as paints and sealers and the substrate is dry.

Efflorescence and laitance should be removed by wire brush and then washed and allowed to dry.

Test areas are important as, although rare, latent salts or other chemicals may cause some discolouration.

APPLICATION

Durotech WRP Concrete Sealer can be applied by brush, roller, spray or poured.

It is essential that the substrate be well saturated, i.e. wet soaked.

For best result, apply a soaking coat of Durotech WRP Concrete Sealer and allow product to be absorbed. Immediately thereafter, while still wet, apply a second soaking application and allow the product to be absorbed. This process can be repeated several times to ensure that sufficient product has been absorbed. The product should be, in the first instance, applied wet on wet. Then allow the product to dry for 24 hours and apply a final soaking coat.

If the product is to be used as an anti-graffiti protection coat, follow the above procedure but ensure sufficient product is used to give a film across the surface.

COLOURS

Durotech WRP Concrete Sealer is a clear product and dries to a low gloss.

COVERAGE

As a general guide the coverage rate for Durotech WRP Concrete Sealer is:

- Ceramic tiled areas: 6m² per Lt - concentrated on the grout lines.
- Terracotta tiled areas: 3m² per Lt per coat.
- Face brick: 4m² per Lt per coat.
- Highly porous areas: 2m² to 3m² per Lt per coat.
- Anti-Graffiti Coating: 2m² to 3m² per Lt per coat.

Note: the required use of product is dependent upon the type, porosity and profile of the surface. The above is given as a guide only. Test areas are recommended.

Our recommendation is to err on the use of additional material as the initial absorption, wet on wet, is very important. Once cured, the absorption of additional material is greatly reduced.

DRYING AND CURING

Drying and curing of the product is affected by type, dryness and porosity of the surface, temperature, humidity, ventilation, climate conditions and application technique and therefore drying and curing can only be given as a guide.

At 25°C and 50% RH (per coat)

- Touch dry: 2 to 4 hours
- Set: 4 to 6 hours
- Full cure: 12 to 24 hours.

Service Temperature: 0°C to 50°C

Application Temperature: 5°C to 30°C

STORAGE

Durotech WRP Concrete Sealer should be stored in a cool, dry place. Keep all sources of ignition away from the product. Store in well-sealed metal containers. Shelf life is up to 12 months in unopened or undamaged containers. Available in 4 Lt and 15 Lt pails.

TILING, TOPPING OR TOP COATING

Not recommended as product is usually left exposed. If area is to be tiled or topped, then we would recommend the use of Durotech's conventional waterproofing membranes.

SAFETY AND PRECAUTIONS

Sealed surfaces may be slippery when wet. The use of Solvent resistant gloves, mask and eye protection is recommended. Observe the safety precautions on the product data sheet and safety data sheet. It is a class 3 dangerous goods must be declared prior to the transportation of the product. Product is flammable. Keep all ignition sources away.

For full safety data refer to the products Safety Data Sheet. Observe precautions as per label.

DUROTECH INDUSTRIES



"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attachments and suggests that the recipient check this document and any attached files for the presence of viruses."