

DUROTECH DUROGLAZE PRO

100% Neutral Cure Silicone Sealant



DESCRIPTION

Durotech Duroglaze Pro is a premium, neutral-cure silicone sealant designed for high-performance use. It is ideal for various glazing, weatherproofing, and specialized trade applications.

FEATURES

- Neutral cure
- Highly flexible $\pm 25\%$
- Excellent weathering
- Long term durability
- Superior adhesion
- Exceptional adhesion
- Non-slumping
- UV Stable

USES

- General purpose glazing
- Curtain walls
- Construction joints
- Building claddings
- Perimeter sealing of door and window frames

Provides excellent adhesion to

- Glass
- Aluminium
- Steel
- Concrete
- Stainless steel
- Ceramic tiles
- Painted and powder coated surfaces*
- Natural and reconstituted stone*
- Most plastics*

TECHNICAL INFORMATION

Physical Properties	Typical value
Elongation	400%
Hardness (Shore A)	- 30
Joint Movement	$\pm 25\%$
Tensile Strength KHF/CM2 (MPA)	20 (2.0)
Cure Method	- Neutral
Skin Time @ 20°C & 50% RH	8-10 min

SUBSTRATE PREPARATION

All surfaces must be clean, dry, sound and free from dust, oil, rust, old sealant or any other contamination.

Glass and metal should be cleaned with methylated spirits. Solvent should be wiped from the surface with a clean dry cloth.

JOINT DESIGN

Open cell polyethylene backing rod shall be used to control the depth of the joint sealant application to the recommended thickness. Correct joint design is necessary to ensure sealants do not split or tear.

The size of the closed cell backing rod used shall allow for 25% compression when inserted into the joint.

JOINT WIDTH

6mm to 10mm
10mm to 20mm
20mm to 25mm

JOINT DEPTH

Equal to joint width
10mm
Half of joint width

COVERAGE

Meters per 300ml cartridge (approx.)

		Joint Width (mm)						
Joint Depth		6	8	10	12	15	20	25
	6mm	8.3	6.3	5	4.1	3.3	2.5	2
	8mm	-	4.6	3.7	3.1	2.5	1.8	1.5
	10mm	-	-	3	2.5	2	1.5	1.2
	12mm	-	-	-	2.1	1.6	1.2	1

APPLICATION

Durotech Duroglaze Pro sealant shall be installed using conventional caulking tools, materials and methods.

1. Cut tip off cartridge.
2. Cut nozzle to the desired bead size at 45° angle.
3. Apply sealant into joint ensuring wetting of both sides.
4. Dry tool sealant immediately to a smooth finish.
5. Remove excess sealant immediately with cloth and solvent (eg. mineral turpentine).

CLEAN UP

- Not to be used as a structural glazing sealant.
- Not paintable.
- Not suitable for certain rubber products where bleeding of plasticiser may occur.
- Not to be used for aquariums.
- Not to be used for polycarbonate plastic sheeting
- Not to be used for joints subjected to permanent water immersion.
- Not to be applied on any substrate containing bitumen.
- Do not use as a trafficable sealant.

PACKAGING

300ml cartridges, 20 cartridges per carton.

COLOUR

Matt Black

SHELF LIFE

12 months minimum, when stored in cool dry conditions below 28°C.

PRECAUTION

Keep out of reach of children. This product emits Methyl Ethyl Ketoxime (MEKO) whilst curing. Wear suitable protective clothing, gloves and eye/faceprotection. Uncured sealant may cause skin, eye and respiratory system irritation. Use only in well ventilated areas.

In case of contact with eyes, rinse immediately with plenty of water and contact a Doctor or Poisons Information Centre (Ph 13 11 26). In case of skin contact, wash affected area with hand cleaner followed by soap and water.

Material Safety Data Sheets must be read and understood prior to using.

Durotech Industries

VICTORIA

34 Indian Drive Keysborough
Victoria 3173

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

NEW SOUTH WALES

14 Essex st, Minto, Sydney
NSW 2566

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

QUEENSLAND

16 Export Drive Molendinar,
Gold Coast 4214

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

SOUTH AUSTRALIA

348 Richmond Road
Netley Australia

Tel: 1300 434 272

sales@durotechindustries.com.au
www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attachments and suggests that the recipient check this document and any attached files for the presence of viruses."



@DUROTECHINDUSTRIES.COM.AU