



# DUROBUILD HB

SINGLE COMPONENT POLYMER MODIFIED, HIGH BUILD REPAIR MORTAR

## PRODUCT INFORMATION

### Introduction

DUROBUILD HB is a single component polymer; cementitious medium weight repair mortar. When mixed with specified amount of water, a gray trowelable mortar results, it is ideal for high build applications on inverted or vertical surfaces. DUROBUILD HB can be applied up to 50mm thick in one pass without formwork. Concrete repair mortar is specially formulated with fibre reinforced to produce shrinkage free mortar giving a smooth finish with excellent adhesion and very good water resistant properties.



### APPROPRIATION

- ◆ Repair of damaged, weak or de bonded concrete
- ◆ Repair of honey combed concrete & Crack filler for concrete
- ◆ Patch work repair on horizontal, vertical and overhead surfaces
- ◆ Replacement of concrete suffering from attack of chlorides or sulphates
- ◆ Replacement of concrete spalled or chipped



### CHARACTERISTICS

- ◆ Premixed powder, which requires only on site addition of water
- ◆ High bond strength to prepare surfaces
- ◆ Durable low permeability and weather proof & Non slumping
- ◆ Resistance to carbonation and attack by chlorides

### TECHNICAL DATA AND PROPERTIES

Standard Confirms to	ASTM C 387:77A Din 1048 & DIN 1045 Class B
Color and Appearance	Grey Powder
Density	1.65
Compressive Strength @ 28 days	43.9N/mm <sup>2</sup>
Flexural Strength @28Days	8.9N/mm <sup>2</sup>
Tensile Strength @ 28Days	3.71N/mm <sup>2</sup>
Bond Strength @28 Days	<26N/mm <sup>2</sup>
Water Absorption	0.95%
Pot Life @ 25°C	30min
Recommended Application thickness	10-50mm/ layer

## PRODUCT MANAGEMENT

- ◆ Surface preparation: The surface of the concrete to be repaired should be sound and uncontaminated. The decayed or damaged area should be saw cut, keeping the sides of the area as square as possible. Loose materials must be removed carefully using suitable means such as sharp tools chipping hammers. If the reinforcement is corroded make sure that the back of the steel is completely exposed. Then clean the steel to bright metal condition.

### Priming:

- ◆ Reinforcement steel – must be fully exposed and thoroughly cleaned around the whole circumference during preparation. By using Duroguard RP – Rust remover
- ◆ Grit blasting is also a preferred method. The steel should then be coated with Durobuild ZR – Zinc rich epoxy primer.
- ◆ Concrete - If the concrete damaged is severe and is due to chloride attack, before applying the Durobuild HB a bonding coat with epoxy bond is advisable. For Durobuild HB to achieve optimum bond in the fresh and cured states, it should be applied when the bonding agent is still tacky. For normal priming on concrete surface it recommended to use Durobond – bonding agent to obtain maximum bonding strength.
- ◆ Mixing: hand or mechanical mixing can mix Durobuild HB. For hand mixing, quantities not greater than 10 kg may be mixed at one time. Slowly add the Durobuild HB powder to clean gauged water, working well to produce a smooth mortar. The consistency of the mix can be adjusted by the addition of more powder or water necessary.
- ◆ Placing and finishing: Whilst the primer is still tacky, apply the mortar mix and compact well. Application can be by a trowel or a rubber gloved hand to force the material in place. Durobuild HB can be applied at a thickness of 40mm at one pass on vertical and overhead surfaces. High build application can be achieved by using form work. While applying multi-layers, the previous layer should be crosshatched and allowed to set before applying the next coat.

### Curing:

Durobuild HB should be cured in accordance with good concrete practice by applying of a suitable curing membrane or by covering the work with properly secured plastic sheeting. Protection against rapid drying from wind, sun or excessive heat is necessary.

Cleaning Clean tools with water immediately after use.

## PACKING AND SHELF LIFE

- ◆ Durobuild HB is available in 25 kg bags. Up to 12 months in unopened containers, Keep out of direct sunlight and moisture.

## HEALTH & SAFETY

- ◆ DUROBUILD HB contains no hazardous substances; however it should not be allowed to come into contact with skin and eyes. Wear suitable protective gloves and goggles whilst handling. When in contact with the skin and eyes, wash thoroughly and immediately with warm water. If swallowed seek medical attention. For more details, please refer to the MSDS released on each Durotech product.



14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177

+61 2 9475 5059

sales@durotechindustries.com.au

[www.durotechindustries.com.au](http://www.durotechindustries.com.au)

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.