

# DUROSEAL 25LM



## DESCRIPTION

Duroseal 25LM is polyurethane based one component sealant for construction. Resistance to surface movements.

## APPLICATION FIELD:

It is used at interior and exterior expansions joints in buildings, all vertical & horizontal dilatations between prefabricate elements in high buildings, towers, terrace dilatations, wood, metal-based joints as a joint waterproofing sealant.

## Removal

Wet sealant can be cleaned with ethyl acetate or other suitable solvents. Dry sealant only removed by mechanical applications.

## SPECIFICATIONS:

- Suitable for outdoor usage
- UV resistance
- Paint applicable
- Resistance to different weather conditions (-300C / + 1200C)
- Perfect adhesion
- Create smooth surface

## TECHNICAL INFORMATION

Colour	White, Grey
Density	1.40 gr/cm <sup>3</sup>
Working Temperature	+50C/ + 300C
Shore Hardness	25
Hardness Time	24 hours for 2mm
Movement Accommodation Factor	25%
Skinning Time	60 minutes
Flexibility	>600%
UV Resistance	Good
Max. Joint Edge Width	4 cm
Shelf Life	12 months

## PACKAGING:

600ml Sausage ..... 20 per carton



## APPLICATION:

Surface preparation: the joint edges must be clean, all oil, dust, dirt, and any other materials that may be used before must be removed. Water affects the Duroseal 25LM so joint edges must be dry and Duroseal 25LM must be protected from water unless the chemical hardness occurred. Duroseal 25LM can be applied without primer application. Polyethylene wicks must be used for filling to avoid adhesion of sealant to the bottom of joint edges. This gives ability for two way movement. Wick's diameter should be bigger than 20-25% of joint edge's diameter. Width and deep of the edge should not be less than 5mm. Up to 15mm; the width size of the edge should be equal to its deep size. For wider joint edges, the deep size adjusted to 20-25mm. For hand applications; place the sealant Duroseal 25LM into the gun and inject the sealant into the joint without causing any air bubble.

## STORAGE

Kept in sealed drums, storage temperature should be normal room temperature to ensure max shelf life (12 month). Production date is on label.

## HEALTH AND SAFETY:

If it touches with skin wash with water and soap. Do not use the empty packages for the storage of nutriment.

### Durotech Industries Pty Ltd

**Address** 14 Essex Street, P.O Box 5092, Minto,  
NSW 2566

**Phone** +61 2 9603 1177

**Fax** +61 2 9475 5059

**Email** sales@durotechindustries.com.au

**Web** www.durotechindustries.com.au



## DUROTECH INDUSTRIES



*"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attachments and suggests that the recipient check this document and any attached files for the presence of viruses."*

