PRODUCT DATA SHEET

DUROMASTIC P15 UV FIBRE

Engineered Contruction Chemicals
Made In Australia For Over 42 Years

FIBRE REINFORCED MODIFIED URETHANE
MEMBRANE FOR UNDER TILE WATERPROOFING
AS4858:2004 & AS3740:2010 – CLASS III

DESCRIPTION

Duromastic P15 UV FIBRE is a polyurethane modified copolymer acrylic waterproofing membrane specifically formulated for bathrooms, laundries, balconies, terraces and other wet areas. Use Duromastic P15 UV FIBRE prior to installing mortar beds, render or tiling. The membrane forms a grey coloured water resistant elastomeric film with excellent durability.

FEATURES

- UV stable
- Single component, water-based
- Exceptional elongation & crack bridging
- Excellent water resistance
- UV resistant
- High Solids
- Ease of application roller/spray/brush
- Excellent adhesion to concrete, brick
- FC sheeting and render.
- Non-hazardous, low odour

USE AREA

- Exposed roof tops
- Internal & External Wet Areas
- Balconies & Decks
- Bathrooms, Kitchens, Laundries
- Roof Areas(non exposed)
- Planter boxes
- Water retaining structures
- Ponds & water features

TECHNICAL INFORMATION

Drying Time	1-2 hours touch dry		
Coverage	2 x coats at a total minimum coverage of 1.5litre/m²		
Elongation at break	≥500%		
Recoat Time at 25°C, 50% R.H.	2 – 4 hours		
Full Cure at 25°C, 50% R.H.	3 days		
Minimum screed & Tiling time at 25°C, 50% R.H.	24 hours		
Colour	Grey		

Coverage minimum recommended 1.0 Litre/m² per coat, applied as 2 or more coats. This will give a recommended dry film thickness of 1.1mm total.

PACKAGING

- 4 Litre
- 15 Litre





SURFACE

- Concrete and concrete blockwork
- Masonry, brick
- Fibrous cement sheeting

PRIMING

High Moisture dampeRenders, Screeds and substrates: Apply 1 coat of Duromix WB Hibuild as a primer in accordance with Product Data Sheet to the prepared substrate.

Concrete Water Tanks: Apply 2 coats of Duromix WB Hibuild as a primer in accordance with Product Data Sheet to the prepared substrate.

APPLICATION

Do not apply externally if rain is expected presently. Do not apply below 10°C or above 30°C externally. Ensure that the primer coat is completely dry. Apply evenly and check for missed areas and pin-holes. Apply further coats from cross directions after 4 to 6 hours. Do not apply as one coat. Apply down into drainage outlets. Use reinforcing fabric over expansion joints, cracks, all wall and floor junctions, and pipe penetrations. Apply this by first brushing out a layer of membrane (1-2 mm), next lay in the fabric and ensure there are no air bubbles, and the fabric is fully set in without wrinkles. Then brush over with more membrane. Good air flow and warmth will speed drying.

APPLICATION RATES

Use Area	Wet Film Thickness (per coat)	Coats Required	Dry Film Thickness
Wet Area Walls	1.0mm	1	0.6mm
Wet Area Floors	0.8mm	2	1.0mm
External Areas	0.8mm	2	1.0mm
Water Tanks	1.0mm	2	1.2mm

PREPARATION

Remove dirt, dust, loose particles, old adhesives and coatings, grime and unsound concrete. Where possible wash down oily, dirt contaminated, or powdery surfaces with dilute detergent, then rinse and dry thoroughly. Allow new concrete and render to fully cure. Ensure all sheeting and surfaces are dry, stable, sound and fully secured. Fix any rising damp problems beforehand. For timber floor surfaces use fibre cement sheeting as a replacement or cover. Remove or flatten all sharp concrete edges, mortar droppings, screw and nail heads. Prime wall and floor surfaces with Durotech Waterproofing Primer. Etch PVC fittings with plumbers PVC primer. For larger cracks, expansion joints, floor and pipe penetrations wall or hob junctions, seal neatly with neutral cure silicone sealant (smooth curved 12mm bead), and when cured apply membrane fabric reinforcement as explained below.

CLEAN UP

Before drying, clean up with water. Scrape off when dry or use paint stripper for spot removal.

SHELF LIFE

12 months at 20°C in original unopened containers. Protect from freezing

Durotech Industries Ptv Ltd

Address 14 Essex Street, P.O Box 5092, Minto,

NSW 2566

Phone +61 2 9603 1177

Fax +61 2 9475 5059

Fmail sales@durotechindustries.com.au www.durotechindustries.com.au Web



DUROTECH INDUSTRIES













